

M1 Mesh




Black M11




Gray M12




Silver M13



Green M14



Red M15



Blue M16

M1 Mesh Card

Technical Specifications

Color		Fiber Content	Finish	Abrasion	Light-fastness	Cleaning Code	Grade
Black	M11	68% Elastometric 32% Polyester	Soil and Stain Resistant	100,000	Class 4, 160 Hrs.	SW	M1
Gray	M12	68% Elastometric 32% Polyester	Soil and Stain Resistant	100,000	Class 4, 160 Hrs.	SW	M1
Silver	M13	68% Elastometric 32% Polyester	Soil and Stain Resistant	100,000	Class 4, 160 Hrs.	SW	M1
Green	M14	68% Elastometric 32% Polyester	Soil and Stain Resistant	100,000	Class 4, 160 Hrs.	SW	M1
Red	M15	68% Elastometric 32% Polyester	Soil and Stain Resistant	100,000	Class 4, 160 Hrs.	SW	M1
Blue	M16	68% Elastometric 32% Polyester	Soil and Stain Resistant	100,000	Class 4, 160 Hrs.	SW	M1

Fire Retardancy
D-Din EN 1021:2006 part 1 (cigarette test) when tested with non flame retardant foam B3 density (22kg/cu m) minimum. Ignition classification of the upholstery compsoite accoridng to DIN 66084 P-c.

Abrasion
DIN En ISO 105-E04:2009. The rub test uses a wet and dry undyed cotton cloth as an abradent. The resultant staining of the air-dried cotton is then assessed on a scale of 1-5 -the requisite minimum pass grades being 3-4 in dry state and 3 in wet - hence some fabrics two numbers are given.

Colorfastness to Light
BS EN 20 105-B02 uses a filtered Xenon-arc light source with a spectrum approximating that of solar radiation. Assessment is against prescribed set of dyed wool standards by comparing a sample's rate of fading against a scale of 1-8. Each higher number reference is oughly twice as color fast as the preceding one, denoting very poor to very good.

Cleaning Code Definition
SW: Water-Based cleaning agents, foam or pure-water-free solvents (Energine, Carbona, Renuzit or other similar products).

UL GREENGUARD
PRODUCT CERTIFIED FOR LOW CHEMICAL EMISSIONS
UL.COM/GG
UL 2818
GOLD

9to5® seating

9to5 Seating
3211 Jack Northrop Ave.
Hawthorne, CA 90250
Tel: 888.925.SEAT --> 888.925.7328
Fax: 866.925.SEAT --> 866.925.7328